

# PURE

## Technical Report

<b>Size:</b>	5.0 – 6.0 m <sup>2</sup>
<b>Thickness:</b>	1.4 – 1.6 mm
<b>Leather type:</b>	Aniline
<b>Origin:</b>	EU
<b>Tannage:</b>	Vegetable-tanned

		Requirements	Our test
<b>Colour fastness to light*:</b>	BS EN ISO 105-B02	≥ BWS 3	Pass
<b>Colour fastness to rubbing:</b>	BS EN ISO 11640		
	Dry 50 rubs	≥3	Pass
	Wet 20 rubs	≥3	Pass
	Perspiration 20 rubs	≥3	Pass
<b>Tearing strength:</b>	BS EN ISO 3377-1	>20N	Pass
<b>Cigarette + match EU:</b>	BS EN 1021-1 and 2		Pass
<b>Flammability:</b>	TB 117-2013		Pass

### \* Reflecting test results on the leather surface

**Colour fastness to light:** The colour of the leather will become lighter over time. The light fastness index suggests how soon this will take place and is measured on a scale from 1 to 8 (1 = lowest and 8 = highest)

**Colour fastness to rubbing** is measured on a scale from 1 to 5 (1 = lowest and 5 = highest)

Technical specifications on the shade card are guidelines only. The information may change due to changes in production. Check our website for the most up-to-date technical details at [www.sorensenleather.com](http://www.sorensenleather.com)

**PCP:** According to EU Council Directive 76/769/EEC

**AZO dyes:** According to EU Council Directive 76/769/EEC

**Chrome VI:** Our leather does not contain chrome VI

**REACH:** According to European Community Regulation on chemicals and their safe use (EC 1907/2006)

PURE has been awarded the **ECARF Seal of Quality**. So it is certified as an allergy-friendly product.

