

DUNES

Technical Report

Size:	4.5 – 5.5 m ²		
Thickness:	1.1–1.3 mm		
		Requirements	Our test
Colour fastness to light:	DIN EN ISO 105-B02	≥3	3
Colour fastness to rubbing*:	DIN EN ISO 11640		
	Dry 50 rubs	≥3	4
	Wet 20 rubs	≥3	3-4
	Perspiration 20 rubs	≥3	3-4
Tearing load:	DIN EN ISO 3377-1/2	>20N	26,7N
Flexing endurance:	DIN EN ISO 5402-1	20,000	no damage
Cigarette + match:	BS 5852-1 and 2		non-ignition
Cigarette + match:	BS EN 1021-1 and 2		non-ignition
Flammability test:	CA TB 117-2013		non-ignition

*Reflecting test results on the leather surface

Colour fastness to light: The colour of the leather will become lighter over time. The light fastness index suggests how soon this will take place and is measured on a scale from 1 to 8 (1 = lowest and 8 = highest)

Colour fastness to rubbing is measured on a scale from 1 to 5 (1 = lowest and 5 = highest)

Technical specifications on the shade card are guidelines only. The information may change due to changes in production. Check our website for the most up-to-date technical details at www.sorensenleather.com

PCP: According to EU Council Directive 76/769/EEC

AZO dyes: According to EU Council Directive 76/769/EEC

Chrome VI: Our leather does not contain chrome VI

REACH: According to European Community Regulation on chemicals and their safe use (EC 1907/2006)

