

HERO

Technical Report

Size:	5.0 – 5.5 m ²		
Thickness:	0.9 – 1.1 mm		
		Requirements	Our test
Colour fastness to light:	DIN EN ISO 105-B02	≥5	>6
Colour fastness to rubbing*:	DIN EN ISO 11640		
	Dry 500 rubs	≥4	4
	Wet 250 rubs	≥3-4	3-4
	Perspiration 80 rubs	≥ 3-4	4
Finish adhesion:	DIN EN ISO 11644	≥2N	4,3N
Tearing load:	DIN EN ISO 3377-1	>20N	38N
Flexing endurance:	DIN EN ISO 5402-1	50,000	no damage
Cigarette + match:	BS EN 1021-1 and 2	-	non-ignition

*Reflecting test results on the leather surface

Colour fastness to light: The colour of the leather will become lighter over time. The light fastness index suggests how soon this will take place and is measured on a scale from 1 to 8 (1 = lowest and 8 = highest)

Colour fastness to rubbing is measured on a scale from 1 to 5 (1 = lowest and 5 = highest)

Technical specifications on the shade card are guidelines only. The information may change due to changes in production. Check our website for the most up-to-date technical details at www.sorensenleather.com

PCP: According to EU Council Directive 76/769/EEC

AZO dyes: According to EU Council Directive 76/769/EEC

Chrome VI: Our leather does not contain chrome VI

REACH: According to European Community Regulation on chemicals and their safe use (EC 1907/2006)

